

Please direct inquiries to:

Chevron Phillips Chemical Company LP  
Mining Chemicals  
10001 Six Pines Drive  
The Woodlands, TX 77380  
Phone: (832) 813-4876  
[http://www.cpchem.com/enu/specialty\\_chemicals\\_p\\_mining\\_chemicals.asp](http://www.cpchem.com/enu/specialty_chemicals_p_mining_chemicals.asp)  
U.S. and Canada toll free: 1-800-858-4327



## ORFOM<sup>®</sup> SX 11 Solvent Extraction Diluent

ORFOM<sup>®</sup> SX 11 solvent extraction diluent is a highly effective diluent for use in the solvent extraction of metals and is recommended for use in high temperature circuits. SX 11 is useful where a very low aromatic, environmentally desirable diluent is desired. SX 11 diluent has a high flash point and shows good phase disengagement properties. It is manufactured to exacting specifications to ensure consistent hydro metallurgical performance

<b>APPLICATION:</b>	ORFOM <sup>®</sup> SX 11 diluent is a high-performance carrier for commercial solvent extraction processes.
<b>BENEFITS:</b>	ORFOM <sup>®</sup> SX 11 diluent is especially effective in high temperature circuits. It is an excellent replacement for low flash kerosene and other commercial diluents.
<b>AVAILABILITY:</b>	ORFOM <sup>®</sup> SX 11 diluent is currently available in drum, tank truck, and tank car quantities.
<b>MATERIAL HANDLING:</b>	Refer to the Material Safety Data Sheet for complete safety and health information.

Typical Composition (1)	Value
Density (kg/l) at 60 °F (15.6 °C)	0.792
Pounds per Gallon	6.63
Flash Point	
Minimum PMCC (ASTM D56), °F (°C)	210 (99)
Typical PMCC (ASTM D56), °F (°C)	200 (93)
Composition, Typical Volume %	
Iso-paraffins	> 97
Alkyl aromatics	< 0.5
Naphthenes	< 3
Naphthalene	< 0.005
Color, Saybolt	> +20
Distillation, (ASTM D86), °F (°C)	
10%	459 (237)
50%, midpoint	472 (244)
90%	510 (266)
Pour Point (ASTM D97), °F (°C)	-50 (-46)
Reid Vapor Pressure, EPA Equation	< 0.05

(1) Not tested for or reported for individual lots. For informational purposes only.

MSDS # 98110

Revision Date: 05.05.2008



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.