

Please direct inquiries to:

Chevron Phillips Chemical Company LP
Mining Chemicals
10001 Six Pines Drive
The Woodlands, TX 77380
Phone: (832) 813-4876
http://www.cpchem.com/enu/specialty_chemicals_p_mining_chemicals.asp
U.S. and Canada toll free: 1-800-858-4327



ORFOM[®] SX 80 Solvent Extraction Diluent

ORFOM[®] SX 80 is a petroleum distillate that is a higher flash, highly effective diluent for use in the solvent extraction of metals. ORFOM[®] SX 80 diluent shows excellent phase disengagement properties, as well as rapid extraction kinetics. ORFOM[®] SX 80 is manufactured to close specifications to ensure product consistency. Our quality assurance program and dedicated storage assure consistent performance. SX 80 is the global standard for SX plant use.

APPLICATION:	ORFOM [®] SX 80 diluent is a lighter, high-performance carrier for commercial solvent extraction processes.
BENEFITS:	ORFOM [®] SX 80 diluent is an excellent replacement for other commercial diluents. ORFOM [®] SX 80 diluent shows excellent phase disengagement properties, as well as rapid extraction kinetics.
AVAILABILITY:	ORFOM [®] SX 80 diluent is currently available in drum, tank truck, and tank car quantities.
MATERIAL HANDLING:	Refer to the Material Safety Data Sheet for complete safety and health information.

Typical Composition (1)	Value
Density (kg/l) at 60 °F (15.6 °C)	0.82
Pounds per Gallon	6.83
Flash Point	
Minimum PMCC (ASTM D93), °F (°C)	170 (77)
Typical PMCC (ASTM D93), °F (°C)	180 (82)
Composition, Typical Volume %	
Paraffins (Iso and normal paraffins)	55
Alkyl aromatics	20
Naphthenes (Cyclic paraffins)	23
Naphthalene	< 0.56
Color, Saybolt	> +30
Distillation, (ASTM D86), °F (°C)	
10%	422 (217)
50%, midpoint	448 (231)
90%	491 (255)
Pour Point (ASTM D97), °F (°C)	-40 (-40)
Reid Vapor Pressure, psia @ 80 °F (27 °C)	< 0.1
Reid Vapor Pressure, psia @ 100 °F (38 °C)	1.0

(1) Not tested for or reported for individual lots. For informational purposes only.

MSDS # CPC 00250

Revision Date: 04.16.2008



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.