

Chevron Phillips Chemical Company LP
10001 Six Pines Drive
The Woodlands, TX 77380
800-858-4327
Technical Service: 832-813-4862

Chevron Phillips Chemicals International N.V.
Brusselsesteenweg 355
B-3090 Overijse, Belgium
+32 (0) 2 689 12 11

Chevron Phillips Chemicals Asia PTE Ltd.
5 Temasek Boulevard
05-01 Suntec Tower Five
Singapore 038985
+65 6337 9700

PA-18, LV Commercial Grade

Property	Typical Value	Specification	Test Method
Appearance	White to yellow powder with no foreign matter	White to yellow powder with no foreign matter	Visual
Volatiles, wt %	0.6	1.0 max	
Melting Point, °C	123	115 – 135	
Viscosity as its potassium salt at 30 °C, 20 wt% in water, cP		1000 max	
IR Absorbance, abs/g, at: 1779 cm ⁻¹	Comparable to standard	Report	FTIR
1709 cm ⁻¹	Comparable to standard	Report	

Product Number: 1073628/1074092

Revised: 07/02/04

Notice: Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.