Chevron Phillips Chemical Company LP P.O. Box 4910 The Woodlands, TX 77387-4910 800.231.1212



Marlex[®] 5440 Polyethylene

LOW DENSITY POLYETHYLENE (LDPE)

This low density polyethylene is tailored for cast film applications that require:

- Suited for high speed converting
- Good clarity
- Low COF

| Typical | cast film applications include: |
|---------|---------------------------------|
| • | Coextruded film |

General purpose packaging

| Nominal Resin Properties | English | SI | Method |
|-----------------------------|---------|-------------------------|------------|
| Melt Index, 190 °C/2.16 kg | | 2.2 g/10 min | ASTM D1238 |
| Density | | 0.925 g/cm ³ | ASTM D1505 |
| Slip | 1000 | 1000 | |
| Antiblock | None | None | |
| Vicat Softening Temperature | 209 °F | 99 ºC | ASTM D1525 |
| Melting Point | 232 °F | 111 ºC | ASTM D3418 |

| Nominal Cast Film Properties at 1.25 mil ¹ | English | SI | Method |
|---|--|---|------------|
| Haze | 4 % | 4 % | ASTM D1003 |
| Gloss, 60° | 135 | 135 | ASTM D2457 |
| COF | 0.15 | 0.15 | ASTM D1894 |
| Dart | | 80 g/mil | ASTM D1709 |
| Elmendorf Tear MD | | 190 g/mil | ASTM D1922 |
| Elmendorf Tear TD | | 255 g/mil | ASTM D1922 |
| WVTR | 0.90 g/100in ² /day | 14 g/m ² /day | ASTM F1249 |
| OTR | 420 cm ³ /100in ² /day | 6300 cm ³ /m ² /day | ASTM D3985 |

1. Produced using a smooth bore extruder at a rate of 7 lb/in die cast film line

Revision Date: June, 2016

Another quality product from



The Woodlands, Texas

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. Further based in contract, tort or otherwise, in connection with the use of the information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.