

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

Marlex[®] 7120B Polyethylene

LINEAR LOW DENSITY POLYETHYLENE (LLDPE)

This linear low density polyethylene is an ethylene-hexene copolymer tailored for film applications that require:

- Excellent processing characteristics
- Exceptional drawdown
- Use alone or in coextrusions; blends with other polyolefins

Typical blown film applications include:

- Coextrusions
- Blend component to improve drawdown
- Thin gauge applications
- General purpose packaging

Nominal Resin Properties	English	SI	Method
Melt Index, 190 °C/2.16 kg	---	2 g/10 min	ASTM D1238
Density	---	0.919 g/cm ³	ASTM D1505
Slip	1000 ppm	1000 ppm	---
Antiblock	None	None	---
Process Aid	None	None	---

Nominal Blown Film Properties at 1 mil ¹	English	SI	Method
Haze	18 %	18 %	ASTM D1003
Gloss, 60°	65	65	ASTM D2457
COF	0.7	0.7	ASTM D1894
Dart	---	150 g/mil	ASTM D1709
Elmendorf Tear MD	---	300 g/mil	ASTM D1922
Elmendorf Tear TD	---	750 g/mil	ASTM D1922
Tensile Strength at Break MD	6500 psi	45 MPa	ASTM D882
Tensile Strength at Break TD	5500 psi	38 MPa	ASTM D882
Tensile Elongation at Break MD	500 %	500 %	ASTM D882
Tensile Elongation at Break TD	750 %	750 %	ASTM D882
1 % Secant Modulus MD	33000 psi	228 MPa	ASTM D882
1 % Secant Modulus TD	40000 psi	276 MPa	ASTM D882

1. Produced on 3.5 in extruder, 30:1 L/D, 8 in die, 80 mil die gap, 2.5:1 BUR, 440 °F melt temperature

Revision Date: July, 2016

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

Marlex[®] 7120B Polyethylene

LINEAR LOW DENSITY POLYETHYLENE (LLDPE)

This linear low density polyethylene is an ethylene-hexene copolymer tailored for film applications that require:

- Good stiffness at thin gauges
- Good drawdown
- Excellent processability
- Can use straight or in blends with LDPE or HDPE
- High amounts of slip agent

Typical cast film applications include:

- Overwrap
- Coextrusions

Nominal Resin Properties	English	SI	Method
Melt Index, 190 °C/2.16 kg	---	2 g/10 min	ASTM D1238
Density	---	0.919 g/cm ³	ASTM D1505
Slip	1000 ppm	1000 ppm	---
Antiblock	None	None	---
Process Aid	None	None	---

Nominal Cast Film Properties at 1.25 mil ¹	English	SI	Method
Haze	3 %	3 %	ASTM D1003
Gloss, 60°	140	140	ASTM D2457
Dart	---	140 g/mil	ASTM D1709
Elmendorf Tear MD	---	300 g/mil	ASTM D1922
Elmendorf Tear TD	---	550 g/mil	ASTM D1922
Tensile Strength at Break MD	6200 psi	43 MPa	ASTM D882
Tensile Strength at Break TD	4800 psi	33 MPa	ASTM D882
Tensile Elongation at Break MD	580 %	580 %	ASTM D882
Tensile Elongation at Break TD	780 %	780 %	ASTM D882
1 % Secant Modulus MD	29000 psi	200 MPa	ASTM D882
1 % Secant Modulus TD	31000 psi	214 MPa	ASTM D882

1. Produced on 2.5 in extruder, 24:1 L/D, 25 mil. die gap, 520 °F melt temperature

Revision Date: July, 2016

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.