

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP  
P.O. Box 4910  
The Woodlands, TX 77387-4910  
800.231.1212



PREMIUM EXTRUSION AND RIGID PACKAGING RESINS

## Marlex® HHM TR-392 Polyethylene

### MEDIUM DENSITY POLYETHYLENE (MDPE)

This high performance medium density polyethylene is an ethylene-hexene copolymer that is tailored for demanding applications that require:

- Excellent tensile elongation properties
- Outstanding resistance to slow-crack growth
- Very good thermal stability

This resin meets these specifications:

- ASTM D4976 - PE 225
- ASTM D3350, Cell Class PE234320E

Typical applications for HHM TR-392 include:

- Irrigation tubing and/or tape

Nominal Physical Properties <sup>(1)</sup>	English	SI	Method
Density	---	0.939 g/cm <sup>3</sup>	ASTM D1505
Flow Rate (MI, 190 °C/2.16 kg)	---	0.16 g/10 min	ASTM D1238
Flow Rate (HLMI, 190 °C/21.6 kg)	---	20.0 g/10 min	ASTM D1238
Flexural Modulus, 2 % Secant - 16:1 span:depth, 0.5 in/min	90,000 psi	620 MPa	ASTM D790
Tensile Strength at Yield, 2 in/min, Type IV bar	2,800 psi	19 MPa	ASTM D638
Tensile Strength at Break, 2 in/min, Type IV bar	4,700 psi	32 MPa	ASTM D638
Tensile Elongation at Break, 2 in/min, Type IV bar	800 %	800 %	ASTM D638
ESCR, Condition B, (100 % Igepal), F <sub>50</sub>	> 1,000 h	> 1,000 h	ASTM D1693
Brittleness Temperature, Type A clamp, Type I specimen	< -103 °F	< -75 °C	ASTM D746
Thermal Stability	> 428 °F	> 220 °C	ASTM D3350

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1 or ASTM F1473.

Revision Date: June, 2018

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.