

When Performance Matters
Rely on Us!



PERFORMANCE PIPE GAS DISTRIBUTION BROCHURE



Driscoplex® 6500
MDPE Gas Distribution Pipe



Yellowstripe® 8300
HDPE Gas Distribution Pipe



Driscopipe® 8100
HDPE Gas Distribution Pipe

Performance Pipe

Performance Pipe is a name you can trust in gas distribution piping. We specialize in natural gas distribution, liquid propane gas (LPG), propane gas distribution, and yard gas products and fittings.

With more than fifty years of polyethylene pipe manufacturing experience, Performance Pipe has seven ISO 9001 certified manufacturing facilities strategically located across the United States.

The unmatched quality and performance of Performance Pipe polyethylene piping products is further enhanced and strengthened by more than five decades of quality polyolefin plastic resin production from our parent company Chevron Phillips Chemical Company LP.

As active members of the American Gas Association, ASTM International, Gas Piping Technology Committee, Plastics Pipe Institute, American Society of Mechanical Engineers, and American Petroleum Institute, we provide technical expertise and service to these organizations on an ongoing basis.

When you select Performance Pipe gas pipe and fittings, in addition to receiving quality products, you also gain access to our team of experts for technical support and assistance. Topics range from assistance in product applications and capabilities to installation and handling to testing and operating procedures. We are here to help. Our territory sales teams are dedicated to the gas distribution industry and to the service of Performance Pipe's gas distribution product customers.

Products

Performance Pipe's gas piping products are the material of choice for premium medium and high density natural gas distribution, LPG, propane gas and yard gas piping systems. Performance Pipe's products are produced to meet or exceed the manufacturing and material requirements of the latest edition of ASTM D2513 *Standard Specification for Polyethylene (PE) Gas Pressure Pipe, Tubing and Fittings*, or applicable international standards. The pipes meet the requirements of ANSI/NFPA 58 *Standard for the Storage and Handling of Liquefied Petroleum Gases*.

Performance Pipe offers the following gas distribution products:

Driscoplex® 6500 MDPE Gas Distribution Pipe

These medium density polyethylene (MDPE) PE2708 pipes and fittings are used primarily in pressure-rated gas distribution systems. The product is also suitable for LPG, propane, yard gas and most after-meter applications. The product is a solid yellow medium density pipe that meets ASTM D3350 Cell Classification of PE234373E and APWA/ULCC Color Code Standards.





Yellowstripe® 8300 HDPE Gas Distribution Pipe

This high density polyethylene (HDPE) PE4710/PE100 pipe is used primarily in pressure rated gas distribution systems. The product is black pipe with four equidistant yellow stripes. The Yellowstripe® 8300 pipe series meets APWA/ULCC Color Code Standards and has an ASTM D3350 Cell Classification of PE445574C when using HDB or PE445576C using MRS.



Driscopipe® 8100 HDPE Gas Distribution Pipe

This high density polyethylene (HDPE) PE4710/PE100 pipe is also primarily used in pressure rated gas distribution applications. The Driscopipe® 8100 pipe series is a black pipe with a co-extruded yellow-shell that complies with the APWA/ULCC Color Code Standards. The pipe has an ASTM D3350 Cell Classification of PE445574C when using HDB or PE445576C using MRS. The yellow shell helps reflect solar heat, enabling retention of higher strength ambient temperature properties. It also provides improved ability to detect damages and scratches.

Fittings

Performance Pipe manufactures medium density and high density molded butt, socket, and saddle fusion fittings. The fittings are manufactured to meet the same requirements as our pipe series where applicable.

Quality

Performance Pipe's polyethylene piping products for gas are unmatched in quality and performance. In addition to meeting the manufacturing and quality requirements of ASTM D2513 *Standard Specification for Polyethylene (PE) Gas Pressure Pipe, Tubing and Fittings*. Performance Pipe's gas products also meet our own internal quality assurance (QA) and quality control (QC) requirements. These internal QA/QC requirements meet or exceed those required by industry standards. Each product line is continuously monitored throughout the manufacturing cycle to ensure that the product adheres to all internal quality control specifications and the manufacturing standard. All seven of Performance Pipe's manufacturing facilities are certified in accordance with the latest edition of ISO 9001. Individual plant certificates of conformance to ISO 9001 are available upon request.

Sizes

Performance Pipe manufactures its Driscoplex® 6500 pipe product in sized ½" CTS through 12" IPS. For larger diameter gas applications (8" though 24") we recommend our high density polyethylene pipes Yellowstripe® 8300 pipe and Driscopipe® 8100 pipe. Both products are available in 1/2" through 24" (16 mm through 630 mm) outside-diameter-controlled polyethylene pipe and tubing sizes. Specific sizes of pipe and fittings available for each product can be found on Performance Pipe's website at www.PerformancePipe.com.

Available Certifications

Specific sizes of Driscoplex® 6500 (MDPE) pipe, Yellowstripe® 8300 (HDPE) pipe and Driscopipe® 8100 (HDPE) pipe and fittings are available with NSF certification to ASTM D2513, CSA (Canadian Gas Association) B137.4, and the UPC (Uniform Plumbing Code) for yard gas piping, LPG, and other after-meter applications.

Outdoor Storage

Performance Pipe polyethylene gas distribution piping products are protected from UV effects and outdoor exposure to ensure pipe performance requirements are maintained.

Yellow pipes, such as Driscopipe® 8100 HDPE gas distribution pipe and Driscoplex® 6500 MDPE gas distribution pipe, are protected against outdoor exposure through additive formulations and are defined as Code E materials in accordance with ASTM D3350. Yellowstripe® 8300 HDPE gas distribution pipe is defined as a Code C material and as such contains a minimum of 2-3 percent carbon black.

Accelerated laboratory weathering tests were conducted on the formulations that predict the yellow pipe materials are sufficiently stabilized against UV deterioration for unprotected outdoor exposure of at least three years.

Black (ASTM D3350 Code C) gas pipe materials are considered stabilized against UV degradation for unprotected outdoor exposure of at least 10 years per ASTM D2513.

Based on the tests conducted, Performance Pipe provides the following specific unprotected outdoor storage recommendations for Performance Pipe's gas distribution piping products.

- ❑ Driscoplex® 6500 pipe 3 years
- ❑ Driscopipe® 8100 pipe 3 years
- ❑ Yellowstripe® 8300 pipe 10 years

Tracking and Traceability

Performance Pipe polyethylene gas distribution piping products are marked per ASTM D2513 and adhere to Department of Transportation regulations for plastic pipe (49 CFR Part 192, §192.63). ASTM D2513-12ae1 requires a 16 character code generated per ASTM F2897 to be legibly printed on pipe in both alpha-numeric and barcode form for tracking and traceability purposes. This 16 character code and corresponding barcode provides information that identifies Performance Pipe as the manufacturer, our specific production location, production run number, date, pipe or fitting type, and material grade.



Cautions

Polyethylene piping has been safely used in thousands of applications. However, there are general precautions that should be observed when using any product. In this respect, polyethylene piping is no different. Below is a list of some of the precautions that should be observed when using Performance Pipe's gas pipe and fittings.

- **Fusion**

During the heat fusion process, equipment and products can reach temperatures in excess of 450°F (231°C). Caution should be taken to prevent burns.

Do not bend pipes into alignment against open butt fusion machine clamps. The pipe may spring out and cause injury or damage.

Performance Pipe polyethylene piping products cannot be joined with adhesives or solvent cement. Pipe-thread joining and joining by hot air (gas) welding or extrusion welding techniques are not recommended for pressure service.

- **Static Electricity**

High static electricity charges can develop on polyethylene piping products, especially during squeeze-off, when repairing a leak, purging, making a connection, etc.

Where a flammable gas atmosphere and static electric charges may be present, observe all company (pipeline operator, utility, contractor, etc.) safety procedures for controlling and discharging static electricity and all requirements for personal protection. See website for: Performance Pipe Technical Note [Polyethylene Pipe Squeeze Off; PP 801-TN](#).

- **Weight, Unloading and Handling**

Although polyethylene pipe is not as heavy as some other piping products, significant weight may be involved. Care should be used when handling and working around polyethylene pipe. Improper handling or abuse may cause damage to piping, compromise system quality or performance, or cause personal injury. Observe the safe handling instructions provided by the delivery driver. See website for [Performance Pipe Video Gallery](#) to view: *Pipe Loading/Unloading-Truck Driver Safety Video*.

- **Coils**

Coiled PE pipe may be restrained with strapping or shrink-wrap to contain the spring-like energy retained within the coil. Cutting or breaking the strapping or removing the shrink-wrap can result in an uncontrolled release. Take all necessary safety precautions and use appropriate equipment. Observe the safe handling instructions provided by the delivery driver and available on the Performance Pipe website at www.performancepipe.com.

Leak Testing

When testing is required, fuel gas distribution systems should be tested in accordance with applicable codes and regulations and distribution system operator procedures. Observe all safety measures, restrain pipe against movement in the event of catastrophic failure, and observe limitations of temperature, test pressure, test duration, and procedures for making repairs.

Protection against Shear and Bending Loads

Measures such as properly placed, compacted backfill, protective sleeves, and structural support are sometimes necessary to protect plastic pipe against shear and bending loads.

For additional installation information see ASTM D2774, *Underground Installation of Thermoplastic Pressure Piping*.

Locating

Most polyethylene materials are not detectable with standard magnetic locating equipment. When installing PE piping, a method or methods for future pipeline detection should be considered. Gas utilities in the area should always be contacted before the start of any underground installation work such as excavation, trenching, directional boring, etc.

Liquid Hydrocarbon Permeation

PE piping that has been in service conveying fuel gases that include liquid hydrocarbons or otherwise exposed to liquid hydrocarbons can sometimes exhibit a bubbly appearance when melted for heat fusion. This bubbling is the result of the rapid expansion (by heat) and passage of heavier, absorbed hydrocarbon gases through the heated and molten polyethylene material. Studies* have shown that propane concentrations under 0.2% is sufficient to sometimes show some bubbling but is not high enough to affect any significant degradation in strength of the pipe or fusion joint. However, since there currently are no field tests to readily determine the amount of absorbed hydrocarbons in PE pipe and their potential effect on the fusion joint, if bubbles are encountered during a heat fusion process, heat fusion should be abandoned and mechanical connections should be used. Substantial liquid hydrocarbon permeation may impact the hydrostatic strength of polyethylene and thus operating conditions should be also be assessed to determine whether an adjustment to the pipeline pressure is necessary. See additional information on the topic on page 15.

(*S.M. Pimputkar, J.A. Stets, and M.L. Mamoun, "Examination of Field Failures", Sixteenth International Plastics Pipe Symposium, New Orleans, Louisiana, November 1999.)

Gas Permeability and Permeation

Plastics are permeable to gases to varying degrees. Although the constituents of natural gas can permeate through polyethylene, the volume of gas lost through permeation is generally so low as to have an insignificant effect on the handling of natural gas in a piping system. The American Gas Association (AGA) *Plastic Pipe Manual for Gas Service* lists the permeability of PE2708 polyethylene pipe to methane, the primary constituent of natural gas, as 4.2×10^{-3} . Using the AGA factor, one mile of 2" SDR 11 PE2708 pipe carrying 100% methane at 60 psi would lose less than 0.27 ft³ per day. Other constituents of natural gas are typically heavier than methane, thus less permeable through polyethylene. Hydrogen is the exception; however, the concentration of hydrogen in most natural gas is so low that the actual amount of hydrogen permeation would be insignificant.

Joining

- D.O.T. Regulations require that each joint in a gas piping system must be made in accordance with written procedures that have been proved by test or experience to produce strong gastight joints (49 CFR Part 192, §192.273(b)).
- D.O.T. Regulations require that written procedures for butt fusion, saddle fusion, and socket fusion joining of polyethylene gas piping must be qualified before use by subjecting specimen joints to required test procedures (49 CFR Part 192, §192.283(a)).
- D.O.T. Regulations require that all persons who make joints in polyethylene gas piping must be qualified under the operator's written procedures (49 CFR Part 192, §192.285(a)).
- D.O.T. Regulations require that the gas system operator must ensure that all persons who make or inspect joints are qualified (49 CFR Part 192, §192.285(d) & §192.287).

Performance Pipe recommends using Performance Pipe's Fusion Joining Procedures Bulletin [PP-750 Heat Fusion Joining Procedures and Qualification Guide](#) when making heat fusion joints with our 6500, 8300 and 8100 Series gas piping products. When PP-750 is used to join Performance Pipe polyethylene gas pipe and fittings, Performance Pipe fusion joining procedures are qualified in accordance with U.S. Department of Transportation Regulations. A copy of PP-750 may be obtained from our website at: www.performancepipe.com.

Other qualified procedures used for butt and saddle fusion of polyethylene gas piping products are ASTM F2620 *Standard Practice for Heat Fusion Joining of Polyethylene Pipe and Fittings*, the Plastic Pipe Institute's, PPI TR-33 *Generic Butt Fusion Joining Procedure for Field Joining of Polyethylene Pipe* and PPI TR-41 *Generic Saddle Fusion Joining Procedure for Polyethylene Gas Piping*.

Squeeze-Off

Squeeze-off is used to control flow in PE pipe by flattening the pipe between parallel bars. Squeeze-off is used for routine and emergency situations. **Do not squeeze-off more than once at the same point on the pipe.** For repeated flow control, throttling, or partial flow restriction, install a valve or an appropriate flow control device.

Complete flow stoppage will not occur in all cases. For larger pipes, particularly at higher pressures, some seepage is likely. If seepage is not permissible, the pipe should be vented in between two squeeze-offs.

Use squeeze-off procedures meeting ASTM F1041 and tools meeting ASTM F1563 with Performance Pipe polyethylene pipes. The combination of pipe, tool, and squeeze-off procedures should be qualified in accordance with ASTM F1734. Correct tool closure stops and closing and opening rates are key elements to squeezing-off without damaging the pipe. Tool closure stops must be correct for the pipe size and wall thickness (SDR). It is necessary to close slowly and release slowly, with slow release being more important.

See Performance Pipe Technical Note [PP-801 Squeeze-Off](#) on our website at: www.performancepipe.com.

Performance Characteristics

Cell Classification

ASTM D3350 *Standard Specification for Polyethylene Plastics Pipe and Fittings Materials* standard cell classification covers the identification of polyethylene materials for pipe and fittings according to a cell classification system. Performance Pipe's gas piping products are listed below.

Table 1: Cell Classifications

| Performance Pipe Product Series | Material Designation Code | ASTM D3350 Cell Classification |
|---------------------------------|---------------------------|--------------------------------|
| Driscoplex® 6500 Pipe (MDPE) | PE2708 | 234373E |
| Driscopipe® 8100 Pipe (HDPE) | PE4710-PE100 | 445574C (445576C*) |
| Yellowstripe® 8300 Pipe (HDPE) | PE4710-PE100 | 445574C (445576C*) |

* When using the Minimum Required Strength (MRS) classification.

Long-Term Strength (HDB)

Performance Pipe's polyethylene piping products for gas distribution are listed with the Plastics Pipe Institute (PPI) and have PPI recommended Hydrostatic Design Basis (HDB) ratings as follows:

Table 2: Hydrostatic Design Basis

| Performance Pipe Product Series | Hydrostatic Design Basis (HDB) 73°F (23°C) | Hydrostatic Design Basis (HDB) 140°F (60°C) |
|---------------------------------|---|--|
| Driscoplex® 6500 Pipe (MDPE) | 1250 psi (8.62 MPa) | 800 psi (5.52 MPa) |
| Driscopipe® 8100 Pipe (HDPE) | 1600 psi (11.03 MPa) | 1000 psi (6.89 MPa) |
| Yellowstripe® 8300 Pipe (HDPE) | 1600 psi (11.03 MPa) | 1000 psi (6.89 MPa) |

HDB by Temperature Interpolation

Elevated temperature properties can be used to determine product capabilities for applications where products will be exposed to elevated temperatures. The Hydrostatic Design Stress for polyethylene is established by testing at 73°F. As with all thermoplastics, when operating temperature increases, pressure capacity decreases.

When determining HDB values, use the interpolation protocol of PPI TR-3 D.2 *Policy for Determining Long-Term Strength (LTHS) By Temperature Interpolation*.

The policy states that, for thermoplastic pipe that is going to be installed at a service temperature greater than 73°F and less than that at which the next HDB has been established, the HDB at the anticipated service temperature can be determined by interpolation.

Table 3: HDB in PSI by Temperature

| Hydrostatic Design Basis , HDB (psi) | | | | |
|--------------------------------------|----------|-------------------|-------------------|-----------|
| Performance Pipe Product Series | 73F Data | 100F Interpolated | 120F Interpolated | 140F Data |
| Driscoplex® 6500 Pipe (MDPE) | 1250 | 1000 | 1000 | 800 |
| Driscopipe® 8100 Pipe (HDPE) | 1600 | 1250 | 1000 | 1000 |
| Yellowstripe® 8300 Pipe (HDPE) | 1600 | 1250 | 1000 | 1000 |

Slow Crack Growth (SCG) Resistance

Resistance to slow crack growth is measured using ASTM F1473 *Standard Test Method for Notch Tensile Test to Measure the Resistance to Slow Crack Growth of Polyethylene Pipes and Resins*. ASTM D2513 requires that all PE materials used in gas distribution service meet a minimum of at least 500 hours when tested per ASTM F1473. The University of Pennsylvania researchers early on concluded that one hour of PENT roughly equated to 13 years of service life.* While that analysis may be limited it does illustrate the tremendous slow crack growth resistance of the current materials.

(* N. Brown. (2007) "Intrinsic Lifetime of Polyethylene Pipelines", Polymer Engineering and Science, 47 (4), pg. 477-480.)

Table 4: Typical PENT Values for resins used in Performance Pipe Product Series

| Performance Pipe Product Series | PENT, hours (ASTM F1473) |
|---------------------------------|--------------------------|
| Driscoplex® 6500 Pipe (MDPE) | >2,000 |
| Driscopipe® 8100 Pipe (HDPE) | >10,000 |
| Yellowstripe® 8300 Pipe (HDPE) | >10,000 |

Rapid Crack Propagation

When a pressurized polyethylene pipe is subjected to an instantaneous and intense impact, a pre-existing or consequently initiated crack or flaw can propagate axially at extremely high speeds. This mode of fracture is referred to as Rapid Crack Propagation, or RCP. It is a property inherent in fracture mechanics of many pipe materials, including polyethylene. Similarly, Rapid Crack Arrest (RCA) is a fast fracture property of the pipe material that arrests the travel of the crack after initiation or before RCP can occur.

While RCP occurrences in PE pipes are extremely rare, the consequences can be significant. Because of the catastrophic nature of a potential RCP event, pipe producers have begun to design pipes and applications such that RCP may be avoided in most circumstances. This has led to the development of several tests, of which the Full-Scale (FS) and Small-Scale Steady State (S4) tests are most relevant.

Full Scale Test (FST) ISO 13478

Polyethylene pipes that are approximately 40 times the diameter in length are pressurized at low temperatures, and failure is initiated through blunt force impact with a striker at one end to initiate a crack. The critical pressure and temperature are directly determined.

Small-Scale Steady State (S4) ISO 13477 and ASTM F1589

The S4 test pipe specimens are typically a minimum of seven times the diameter in length. Specimens are conditioned at the test temperature, and then moved to the S4 test rig where they are sealed at both ends and pressurized with air. A sharp chisel-edged striker impacts the pipe at one end to initiate a fast-running crack. A containment cage around the specimen constrains the outside diameter of the pipe and a series of baffles inserted into the pipe's inside diameter restrains the decompression during crack propagation. The results are correlated to the full scale critical pressure.

Performance Pipe's gas piping products have been tested to ISO 13477 and/or ISO13478 with exceptional RCP resistance.

ASTM Test Values

The charts below show material physical properties, ASTM test methods for the property, and nominal values for Performance Pipe materials used for gas pipe. (Note - Per ASTM D748, the brittleness temperature is less than $<-103^{\circ}\text{F}$ ($<-75^{\circ}\text{C}$), therefore, Performance Pipe's Yellowstripe[®] 8300 pipe, Driscopipe[®] 8100 pipe and Driscoplex[®] 6500 pipe series may be used at operating temperatures down to or below $<-40^{\circ}\text{F}$ ($<-40^{\circ}\text{C}$)). Typical physical properties for each pipe are included below.

**Yellowstripe® 8300 HDPE Gas Distribution Pipe
PE4710-PE100
Typical Physical Property Pipe Data Sheet**

| Property | Unit | Test Procedure | Typical Value |
|---|---------------------|---------------------|--|
| Material Designation | -- | PPI TR-4 | PE4710 PE100 |
| Cell Classification | -- | ASTM D3350 | 445574C 445576C |
| Pipe Properties | | | |
| Density | g / cm ³ | ASTM D1505 | 0.961 (black) |
| Melt Index (MI) Condition 190/2.16 | g / 10 minutes | ASTM D1238 | 0.08 |
| Melt Index (HLMI) Condition 190/21.6 | g / 10 minutes | ASTM D1238 | 7.5 |
| Hydrostatic Design Basis, (73°F) | psi | ASTM D2837 | 1,600 |
| Hydrostatic Design Basis, (140°F) | psi | ASTM D2837 | 1,000 |
| Minimum Required Strength | MPa (psi) | ISO 9080 | 10 (1450) |
| Rapid Crack Propagation Critical Pressure (P _c), 0°C (32°F) ⁽¹⁾ | bar (psi) | ISO 13477 | >12 bar (>174) |
| Color; UV Stabilizer [C] | % | ASTM D3350 | Min. 2% Carbon Black UV stabilized 10 years |
| Pipe Test Category | --- | ASTM D2513 | CEE |
| Material Properties | | | |
| Flexural Modulus @2% strain | psi | ASTM D790 | 150,000 |
| Tensile Strength at Yield | psi | ASTM D638 (Type IV) | >3,500 |
| Elongation at Break 2 in/min., Type IV bar | % | ASTM D638 | >500 |
| Hardness | Shore D | ASTM D2240 | 65 |
| PENT | hrs | ASTM F1473 | 10,000 |
| Manufactured to ASTM D2513 for pipe. Fittings comply with ASTM D2513 and ASTM D3261. | | | |
| Thermal Properties | | | |
| Vicat Softening Temperature | °F | ASTM D1525 | 255 |
| Brittleness Temperature | °F | ASTM D746 | <-103 |
| Thermal Expansion | in / in / °F | ASTM D696 | 1.0 x 10 ⁻⁴ |

(1) RCP properties determined by S4 test on 10 inch DR11.

(2) NOTICE: This data sheet provides typical physical property information for polyethylene resins used to manufacture PERFORMANCE PIPE polyethylene piping products. It is intended for comparing polyethylene piping resins. It is not a product specification, and it does not establish minimum or maximum values or manufacturing tolerances for resins or for piping products. Some of these typical physical property values were determined using compression molded plaques. Values obtained from tests of specimens taken from piping products can vary from these typical values. This data sheet may be changed from time to time without notice. Contact Performance Pipe to determine if you have the most recent edition.

**DRISCOPIPE® 8100 HDPE Gas Distribution Pipe
PE4710-PE100
Typical Physical Property Pipe Data Sheet**

| Property | Unit | Test Procedure | Typical Value |
|---|---------------------|---------------------|---|
| Material Designation | -- | PPI TR-4 | PE4710 PE100 |
| Cell Classification | -- | ASTM D3350 | 445574C 445576C |
| Pipe Properties | | | |
| Density | g / cm ³ | ASTM D1505 | 0.961 (black) |
| Melt Index (MI) Condition 190/2.16 | g / 10 minutes | ASTM D1238 | 0.08 |
| Melt Index (HLMI) Condition 190/21.6 | g / 10 minutes | ASTM D1238 | 8.0 |
| Hydrostatic Design Basis, (73°F) | psi | ASTM D2837 | 1,600 |
| Hydrostatic Design Basis, (140°F) | psi | ASTM D2837 | 1,000 |
| Minimum Required Strength | MPa (psi) | ISO 9080 | 10 (1450) |
| Rapid Crack Propagation Critical Pressure (Pc), 0°C (32°F) ⁽¹⁾ | bar (psi) | ISO 13477 | >12 (>174) |
| Color; UV Stabilizer | --- | ASTM D3350 | Co-extruded yellow shell UV stabilized for 3 years outdoor storage |
| Pipe Test Category | --- | ASTM D2513 | CEE |
| Material Properties | | | |
| Flexural Modulus @2% strain | psi | ASTM D790 | 140,000 |
| Elastic Modulus @ Secant 2% strain (2in/min, Type IV bar) | psi | ASTM D638 | >200,000 |
| Tensile Strength at Yield | psi | ASTM D638 (Type IV) | 3,700 |
| Elongation at Break 2 in/min., Type IV bar | % | ASTM D638 | >700 |
| Hardness | Shore D | ASTM D2240 | 65 |
| PENT | hrs | ASTM F1473 | >10,000 |
| Pipe is manufactured to ASTM D2513. Fittings comply with ASTM D2513 and ASTM D3261. | | | |
| Thermal Properties | | | |
| Vicat Softening Temperature | °F | ASTM D1525 | 255 |
| Brittleness Temperature | °F | ASTM D746 | <-103 |

(1) RCP Properties determined by S4 test on 12 inch DR11 pipe.

(2) NOTICE: This data sheet provides typical physical property information for polyethylene resins used to manufacture PERFORMANCE PIPE polyethylene piping products. It is intended for comparing polyethylene piping resins. It is not a product specification, and it does not establish minimum or maximum values or manufacturing tolerances for resins or for piping products. Some of these typical physical property values were determined using compression molded plaques. Values obtained from tests of specimens taken from piping products can vary from these typical values. This data sheet may be changed from time to time without notice. Contact Performance Pipe to determine if you have the most recent edition.

**Driscoplex® 6500 MDPE Gas Distribution Pipe
PE2708
Typical Physical Property Pipe Data Sheet**

| Property | Unit | Test Procedure | Typical Value |
|---|---------------------|---------------------|--|
| Material Designation | -- | PPI TR-4 | PE2708 |
| Cell Classification | -- | ASTM D3350 | 234373E |
| Pipe Properties | | | |
| Density | g / cm ³ | ASTM D1505 | 0.939 |
| Melt Index (MI) Condition 190/2.16 | g / 10 minutes | ASTM D1238 | 0.18 |
| Melt Index (HLMI) Condition 190/21.6 | g / 10 minutes | ASTM D1238 | 20.0 |
| Hydrostatic Design Basis, (73°F) | psi | ASTM D2837 | 1,250 |
| Hydrostatic Design Basis, (140°F) | psi | ASTM D2837 | 800 |
| Minimum Required Strength | MPa (psi) | ISO 9080 | 8.0 (1160) |
| Rapid Crack Propagation Critical Pressure (P _c), 0°C (32°F) ⁽¹⁾ | bar (psi) | ISO 13478 | 8.5 bar (>123) |
| Color; UV Stabilizer | --- | ASTM D3350 | Yellow UV stabilized for 3 years outdoor storage |
| Pipe Test Category | --- | ASTM D2513 | CDE |
| Material Properties | | | |
| Flexural Modulus @2% strain | psi | ASTM D790 | 90,000 |
| Elastic Modulus @ Secant 2% strain (2in/min, Type IV bar) | psi | ASTM D638 | >86,000 |
| Tensile Strength at Yield | psi | ASTM D638 (Type IV) | 2,800 |
| Elongation at Break 2 in/min., Type IV bar | % | ASTM D638 | >800 |
| Hardness | Shore D | ASTM D2240 | 63 |
| PENT | hrs | ASTM F1473 | >2000 |
| Thermal Properties | | | |
| Vicat Softening Temperature | °F | ASTM D1525 | 227 |
| Brittleness Temperature | °F | ASTM D746 | <-103 |
| Thermal Expansion | in / in / °F | ASTM D696 | 1.0 x 10 ⁻⁴ |
| Manufactured to ASTM D2513 for pipe. Fittings comply with ASTM D2513 and ASTM D3261. | | | |

- (1) RCP Properties determined by full scale test on 8 inch DR11 pipe. See Technical Note PP 842-TN.
(2) NOTICE: This data sheet provides typical physical property information for polyethylene resins used to manufacture PERFORMANCE PIPE polyethylene piping products. It is intended for comparing polyethylene piping resins. It is not a product specification, and it does not establish minimum or maximum values or manufacturing tolerances for resins or for piping products. Some of these typical physical property values were determined using compression molded plaques. Values obtained from tests of specimens taken from piping products can vary from these typical values. This data sheet may be changed from time to time without notice. Contact Performance Pipe to determine if you have the most recent edition.

Design Pressure

The following formula is used to compute the design pressures for polyethylene piping systems for natural gas service at operating temperatures up to but not over 140°F (60°C). For operating temperatures below 73°F (23°C), use 73°F (23°C) Design Pressures.

$$P = \frac{2S}{(DR - 1)} (DF)$$

Where:

P = Design Pressure in pounds per square inch gauge (psig);

S = Hydrostatic Design Basis psi, at pipeline operating temperature; See Table 5.

DF = Design factor (specified in 49 CFR §192.121); See Table 6.

DR= Standard Dimension Ratio

$$DR = \frac{\text{Pipe Nominal Outside Diameter}}{\text{Pipe Minimum Wall Thickness}}$$

Table 5: Hydrostatic Design Basis

| Hydrostatic Design Basis , HDB (psi) | | | | |
|--------------------------------------|----------|-------------------|-------------------|-----------|
| Performance Pipe Product Series | 73F Data | 100F Interpolated | 120F Interpolated | 140F Data |
| Driscoplex® 6500 Pipe (MDPE) | 1250 | 1000 | 1000 | 800 |
| Driscopipe® 8100 Pipe (HDPE) | 1600 | 1250 | 1000 | 1000 |
| Yellowstripe® 8300 Pipe (HDPE) | 1600 | 1250 | 1000 | 1000 |

Table 6: Design Service Factor

| Design Factor by Application | |
|---|-----------------------------|
| Application | Design (service) Factor, DF |
| Gas distribution and transmission per 49 CFR Part 192, ≤12" PE pipe meeting minimum wall thickness requirements per §192.121 and produced after January 22, 2019. | 0.40 |
| Gas distribution and transmission per 49 CFR Part 192, >12" pipe and pipe not meeting the requirements for a 0.40 DF per §192.121 | 0.32 |

Design Pressure Ratings

The Pipeline and Hazardous Materials Safety Administration (PHMSA) issued the Plastic Pipe Rule amending 49 CFR Part 192. The revised §192.121 allows the use of a design factor of 0.40 to calculate the design pressure rating for PE2708 and PE4710 pipes sizes 12" IPS and smaller meeting certain minimum wall thickness requirements and manufactured after January 22, 2019. A 0.32 design factor would continue to be applied to all other PE pipe.

The following table uses the design factors as specified by §192.121. A check should be made to determine if these pressures apply under the state and/or local codes governing the specific application. Use 73°F (23°C) pressure ratings for operating temperatures below 73°F (23°C).

Table 7: Maximum Design Pressure Ratings Performance Pipe Gas Distribution Products

| Maximum Design Pressure Rating per §192.121 for Dry Natural Gas Service | | | | | |
|--|---|--------------------|---------------------|---------------------|---------------------|
| Driscoplex® 6500 Pipe (Design Factor 0.40) PE2708 | | | | | |
| Size(s) | Dimension Ratio (DR) / Wall Thickness [inches] (WT) | 73°F (23°C) (PSIG) | 100°F (38°C) (PSIG) | 120°F (48°C) (PSIG) | 140°F (60°C) (PSIG) |
| ½" CTS | 0.090" WT | 125† | 125† | 125† | 108 |
| 1" CTS | 0.099" WT | 77‡ | 62‡ | 62‡ | 49‡ |
| ½" IPS | DR 9.33 | 120 | 96 | 96 | 77 |
| 1 ¼" IPS | DR 10.0 | 111 | 89 | 89 | 71 |
| ¾" IPS – 12" IPS | DR 11.0 | 100 | 80 | 80 | 64 |
| 3" IPS – 12" IPS | DR 11.5 | 95 | 76 | 76 | 61 |
| 4" IPS – 12" IPS | DR 13.5 | 80 | 64 | 64 | 51 |
| Driscopipe® 8100 and Yellowstripe® 8300 Pipe (Design Factor 0.40) PE4710/PE100 | | | | | |
| Size(s) | Dimension Ratio (DR) / Wall Thickness [inches] (WT) | 73°F (23°C) (PSIG) | 100°F (38°C) (PSIG) | 120°F (48°C) (PSIG) | 140°F (60°C) (PSIG) |
| ½" CTS | 0.090" WT | 125† | 125† | 125† | 125† |
| 1" CTS | 0.090" WT | 89‡ | 70‡ | 56‡ | 56‡ |
| | 0.101" WT | 101‡ | 79‡ | 63‡ | 63‡ |
| ½" IPS | DR 9.33 | 125† | 120 | 96 | 96 |
| ¾" IPS – 12" IPS | DR 11.0 | 125† | 100 | 80 | 80 |
| 6" IPS – 12" IPS | DR 13.5 | 102 | 80 | 64 | 64 |
| > 12" IPS | DR 11.0 | 100† ‡ | 80‡ | 64‡ | 64‡ |
| | DR 17 | 64‡ | 50‡ | 40‡ | 40‡ |
| † 49 CFR Part §192.121 limits design pressure to 125psig for pipe ≤12" IPS and 100psig for >12"IPS. | | | | | |
| ‡ Uses a Design Factor of 0.32; does not meet the size or wall requirement of 49 CFR Part §192.121 for 0.40. | | | | | |

Liquid Hydrocarbon Effect on Pressure Ratings

Dry gaseous hydrocarbons have no adverse effect on the expected service life. Liquid hydrocarbons such as gasoline and gas condensates will permeate the wall and reduce hydrostatic strength, but do not degrade the material. Upon evaporation of the hydrocarbon, the pipe will regain its original physical properties. PE pipe to be exposed continuously to liquid hydrocarbons may require a reduction of the pipe's design pressure rating. Per ANSI GPTC Z380.1 *Guide for Gas Transmission, Distribution, and Gathering Piping Systems*, a 0.5 application factor is recommended as shown in the equation below.

$$P_{de-rated} = P_{\S 192.121} \times 0.50$$

Cold Bending Radius

The allowable cold bending radius for Driscoplex® gas distribution pipe is dependent upon the pipe OD, DR and the presence of fittings in the bend. See Performance Pipe's Technical Note [PP-819-TN Field Bending of Driscoplex® PE Piping](#).

Table 8: Allowable Cold Bending Radius

| Pipe Dimension Ratio | Allowable Cold Bending Radius |
|---------------------------------------|-------------------------------|
| 9 or less | 20 times the pipe OD |
| >9 to 13.5 | 25 times the pipe OD |
| 13.5 or greater | 27 times the pipe OD |
| Fitting or flange present in the bend | 100 times the pipe OD |

Special Considerations for Plowing and Planting

Plowing and planting involve cutting a narrow trench and feeding the pipe into the trench through a shoe or chute fitted just behind the trench cutting equipment. The shoe or chute feeds the pipe into the bottom of the cut. The minimum bend radius of the pipe through the shoe may be tighter than the minimum bend radius of the pipe used for a permanent long-term installation, but it must not be so tight that the pipe kinks. Table 9 presents the minimum short-term bend ratio for applications such as plowing and planting. The pipe's path through the shoe or chute should be as friction free as practicable to reduce additional outerfiber tensile stresses. Generally plowing and planting is limited to 12" and smaller pipes.

Table 9: Minimum Short-term Cold Bending Radius

| Pipe Dimension Ratio | Minimum Short-Term bending Radius |
|----------------------|-----------------------------------|
| 9 | 10 |
| >9 to 13.5 | 13 |
| >13.5 to 17 | 17 |

Propane (LPG) Gas Service

The Office of Pipeline Safety Advisory Bulletin No. 73-4, dated April 1973, states, "It is the operator's responsibility to assure the integrity of the plastic pipe selected for use in the piping system, and this should be based on a favorable recommendation from the manufacturer. Therefore, the Federal minimum safety standards do permit the use of plastic in a properly engineered underground system of LPG distribution conforming to the limitations of these regulations." Driscoplex® 6500 pipe (PE2708), Driscopipe® 8100 pipe (PE4710) and Yellowstripe® 8300 pipe (PE4710) series products meet the requirements of ANSI/NFPA 58 *Standard for the Storage and Handling of Liquefied Petroleum Gases*.

The Plastics Pipe Institute has made the following "Use Recommendation" for polyethylene piping systems for commercial propane systems (PPI Technical Report TR-22):

The information collected indicates that polyethylene plastic piping is satisfactory for transporting LPG and its major component, propane gas. This information also indicates that pressure design parameters based on propane gas should be adequate and reasonable. However, until more information is available, these use recommendations cover only commercial propane vapor in detail.

1. The polyethylene plastic pipe, tubing and fittings should be only those specific types designated as PE2708 or PE4710 and meeting the appropriate requirements of ASTM D2513.
2. A Hydrostatic Design Basis of 1000 psi should be used in the design of polyethylene pipe systems for propane gas distribution at pipe temperatures of 73°F or lower. The long-term hydro static strength measurements should be made in accordance with ASTM D2837.
3. Polyethylene should be used only in underground propane gas distribution systems designed to operate at internal pressures and temperatures such that condensation will not occur.

It is also recommended that operating pressures be limited to 30 psig or less.

In cases where condensation does occur in a propane system or propane enriched system and the presence of condensation is of relatively short duration, there is no indication of loss of physical integrity or observable change in polyethylene pipe. Under actual operating conditions, in a properly designed system, the pressures and temperatures are such that revaporization of any propane condensates will usually occur. Experience with propane liquids in polyethylene shows that there is no cumulative effect of intermittent, short duration exposure of propane condensate in polyethylene. For additional information, see PPI Technical Report TR-22. Exposure to liquefied propane condensates for extended periods may affect joining.

Mercaptans

Mercaptans are a group of organic compounds containing a Sulfur-Hydrogen bond that have a distinct odor in small concentrations. Natural gas is an odorless hydrocarbon. Natural gas carriers and distributors add mercaptans to natural gas to warn of leaks and to alert the presence of natural gas atmospheres. New plastic pipes have the tendency to absorb mercaptans, causing the odor to fade or become faint. The effect is not long term and after a period of time the distinctive odor of mercaptan is readily detected when released.

Mercaptan enriched natural gas has the possibility of inducing a phenomenon known as "odor fatigue." The condition can cause nasal passages to become saturated with the smell of gas over time, making it difficult to continue to detect the mercaptan odor.

When Performance Matters Rely on *Performance Pipe*

CONTACT INFORMATION:

Performance Pipe
A Division of Chevron Phillips Chemical Company LP
5085 W. Park Blvd, Suite 500
Plano, TX 75093
Phone: 800-527-0662

Technical Services
Phone: 972-599-6632
Email: pipe-techsupport@cpchem.com

Visit Performance Pipe on the web for the latest literature updates.
www.performancepipe.com

NOTE: By using any Technical Information contained herein, Recipient agrees that said Technical Information is given by Performance Pipe, a division of Chevron Phillips Chemical Company LP for convenience only, without any warranty or guarantee of any kind, and is accepted and used at your sole risk. Recipients are encouraged to verify independently any such information to their reasonable satisfaction. As used in this paragraph, "Technical Information" includes any technical advice, recommendations, testing, or analysis, including, without limitation, information as it may relate to the selection of a product for a specific use and application.