

CTS = Copper Tube Size

Nominal Size (Inches)	Dimension Ratio	Outside Diameter (Inches)	Minimum Wall (Inches)	Max Design Pressure @ 73°F per CFR Part 192.121 (psi)	Weight (lbs) per 100 ft.	Coil/Joint (feet)	Nominal Packing Dimensions	Number Coils / Joints Per Pallet or Bundle	Pallet/ Bundle Footage	Number Pallet / Bundles Per Truck	48 ft. Truck
							ID / OD / Width				
1/2"	*N/A	0.625	0.090	125	6.5	500' 1000'	30"/43"/3-2/3" 30"/43"/6-1/2"	18 11	9,000' 11,000'	26	234,000' 286,000'
1"	*N/A	1.125	0.099	77**	14	500'	30"/43"/11"	6	3,000'	26	78,000'

IPS = Iron Pipe Size

Nominal Size (Inches)	Dimension Ratio	Outside Diameter (Inches)	Minimum Wall (Inches)	Max Design Pressure @ 73°F per CFR Part 192.121 (psi)	Weight (lbs) per 100 ft.	Coil/Joint (feet)	Nominal Packing Dimensions	Number Coils / Joints Per Pallet or Bundle	Pallet/ Bundle Footage	Number Pallet / Bundles Per Truck	48 ft. Truck
							ID / OD / Width				
1/2"	DR 9.33	0.840	0.090	120	9.1	500'	30"/43"/6-1/2"	11	5,500'	26	143,000'
3/4"	DR 11	1.050	0.095	100	12	500'	30"/43"/10-3/8"	7	3,500'	26	91,000'
1"	DR 11	1.315	0.120	100	19	500'	30"/43"/12-1/2"	5	2,500'	26	65,000'
1 1/4"	DR 10	1.660	0.166	111	34	500'	48"/72"/7-1/2"	12	6,000'	7	42,000'
1 1/2"	DR 11	1.900	0.173	100	40	500'	48"/75"/8-1/2"	8	4,000'	7	28,000'
2"	DR 11	2.375	0.216	100	63	500'	52"/78"/13"	7	3,500'	7	24,500'
			0.318	100	137	500'	70"/96"/23-3/4"	4	2,000'	6	12,000'
			0.304	95	131	40'	soft bundles	50	2,000'	14	28,000'
3"	DR 11.5	3.500	0.304	95	131	500'	70"/96"/23-3/4"	4	2,000'	6	12,000'
			0.409	100	226	500'	70"/93"/41"	2	1,000'	6	6,000'
			0.391	95	217	40'	soft bundles	30	1,200'	14	16,800'
			0.333	80	188	1,000'	84"/116"/49"	upright	1,000'	8 coils	8,000'
4"	DR 13.5	4.500	0.333	80	188	40'	soft bundles	30	1,200'	14	16,800'
			0.602	100	490	40'	soft bundles	13	520'	14	7,280'
			0.576	95	471	500'	84"/120"/50"	upright	500'	8 coils	4,000'
			0.491	80	407	40'	soft bundles	13	520'	14	7,280'
6"	DR 13.5	6.625	0.491	80	407	450'	84"/120"/50"	upright	500'	8 coils	4,000'
			0.784	100	831	40'	soft bundles	9	360'	10	3,600'
			0.750	95	799	40'	soft bundles	9	360'	7	2,520'
			0.639	80	690	40'	soft bundles	9	360'	7	2,520'
8"	DR 11.5	8.625	0.639	80	690	40'	soft bundles	9	360'	7	2,520'
			0.977	100	1291	40'	soft bundles	9	360'	7	2,520'
			0.935	95	1241	40'	soft bundles	9	360'	7	2,520'
10"	DR 11.5	10.750	0.935	95	1241	40'	soft bundles	9	360'	7	2,520'
			1.109	95	1746	40'	bulk packs	8 joints/layer	320'	6	1,920'
12"	DR 13.5	12.750	0.944	80	1509	40'	bulk packs	8 joints/layer	320'	6	1,920'
			0.944	80	1509	40'	bulk packs	8 joints/layer	320'	6	1,920'

This product flyer is intended for reference purposes. It should not be used in place of the advice from a licensed professional engineer. 49 CFR §192.121 indicates a 0.40 Design Factor (DF) may be used on ≤12" IPS PE2708/PE4710 pipes produced after January 22, 2019 meeting the minimum wall thickness requirements per §192.121. Unless otherwise noted, Design Pressure Ratings are calculated based on an operating temperature of 73°F and a Design Factor (DF) of 0.40. 49 CFR Part §192.121 also limits design pressure to 125 psig for pipe ≤12" IPS and 100 psig for >12" IPS. Pipe weights are calculated in accordance with PPI TR-7. Nominal OD and Minimum wall plus 6% is used in estimating fluid flow. Actual ID will vary. When designing components to fit the pipe ID, refer to pipe dimensions and tolerances in the applicable pipe manufacturing specification.

*N/A - The wall thickness is minimum per D2513 and not a function of DR.

**Uses a Design Factor of 0.32; does not meet the minimum wall thickness or size requirements of 49 CFR §192.121 for Design Factor of 0.40.

Blue signifies AUTO COIL Products