

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.852.5531



Synfluid® PAO 10 cSt

Highly Branched Isoparaffinic Polyalphaolefin

Handling Maximum temperatures of 65 °C (149 °F) for handling and ambient for long-term storage are recommended. For specific instructions on handling, see SDS.

Typical Properties

Property	Test Method	Typical Value
Kinematic Viscosity, cSt @ 100°C, 212°F	ASTM D7042 or D445	9.64
Kinematic Viscosity, cSt @ 40°C, 104°F	ASTM D7042 or D445	61.0
Kinematic Viscosity, cSt @ -40°C, -40° F	ASTM D7042 or D445	30,704
Viscosity Index	ASTM D2270	141
Pour Point, °C (°F)	ASTM D5950	-58 (-72)
Flash Point (COC), °C (°F)	ASTM D92	263 (503)
Fire Point (COC), °C (°F)	ASTM D92	299 (570)
Volatility, Noack, wt%	ASTM D5800	3.5
Specific Gravity, 60°/60°F, 15.6°/15.6°C	ASTM D4052	0.835
Bromine Index, mg Br/100 g	ASTM D2710	64
Density, lb/gal	ASTM D7042	6.968
Color, Pt-Co	ASTM D5386	0

SDS # 10000013642

Revision Date April 2017

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. **CHEVRON PHILLIPS CHEMICAL COMPANY LP DOES NOT MAKE, AND EXPRESSLY DISCLAIMS, ALL WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, REGARDLESS OF WHETHER ORAL OR WRITTEN, EXPRESS OR IMPLIED, OR ALLEGEDLY ARISING FROM ANY USAGE OF ANY TRADE OR FROM ANY COURSE OF DEALING IN CONNECTION WITH THE USE OF THE INFORMATION CONTAINED HEREIN OR THE PRODUCT ITSELF.** The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.